

Average properties				
Grade	Universal Plotter paper			
Pulp	ECF			
Medium	neutral			
Substance	80	90	g/m ²	NF EN ISO 536
Thickness	104	117	microns	NF EN ISO 534
Bulk	1,30	1,30	cm ³ /g	NF EN ISO 534
Whiteness	168	168	CIE.	NF ISO 11475
Bendtsen roughness	145	145	ml/min	ISO 8791-2
Absolute humidity	5,6	5,6	%H ₂ O	NF EN ISO 20287
Relative humidity	41	41	dans l'air	sabre
Opacity	94	96	%	NF ISO 2471
Kajaani formation	90	90		
Permanence	ISO 9706			NF EN ISO 9706

13/03/2019