



(Contd. on page 2) EU



Page 2/6 Printing date 22.02.2023 Revision: 22.02.2023 Version number 1

Trade name: QG 88xx Series; xx = 00; 01; 02; 03; 15; 10; 20; 21; 30; 31; 32; 40; 41; 50; 60; 61; 62; 70; 80 (var. colours)

· **vPvB:** Not applicable.

(Contd. of page 1)

# SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Mixture of substances listed below with nonhazardous additions.

EC number: 916-899-6	Reaction products of tetrazotized 5-amino-2-[(E)-2-(4- amino-2-sulfophenyl)ethenyl]benzenesulfonic acid with 6- amino-4-hydroxynaphthalene-2-sulfonic acid and 4-amino- 5-hydroxynaphthalene-2,7-disulfonic acid in 2-[bis(2- hydroxyethyl)amino]ethanol Skin Sens. 1B, H317	0-<10%
CAS: 18472-87-2 EINECS: 242-355-6 Reg.nr.: 01-2120115907-54	C.I. Acid Red 92 Aquatic Acute 1, H400	0-<5%
CAS: 52-51-7 EINECS: 200-143-0 Reg.nr.: 01-2119980938-15	bronopol (INN) Eye Dam. 1, H318; Aquatic Acute 1, H400 (M=10); Aquatic Chronic 1, H410 (M=1); Acute Tox. 4, H302; Acute Tox. 4, H312; Skin Irrit. 2, H315; STOT SE 3, H335	<0.1%
CAS: 26530-20-1 EINECS: 247-761-7	<pre>2-octyl-2H-isothiazol-3-one Acute Tox. 3, H301; Acute Tox. 3, H311; Acute Tox. 2, H330;  Skin Corr. 1, H314; Eye Dam. 1, H318; Aquatic Acute 1, H400 (M=100); Aquatic Chronic 1, H410 (M=100);  Skin Sens. 1A, H317, EUH071 ATE: LD50 oral: 125 mg/kg LD50 dermal: 311 mg/kg LC50/4 h inhalative: 0.27 mg/l Specific concentration limit: Skin Sens. 1A; H317: C ≥0.0015 %</pre>	0.0015-<0.005

## SECTION 4: First aid measures

· 4.1 Description of first aid measures

· After inhalation: Supply fresh air; consult doctor in case of complaints.

- · After skin contact: Generally the product does not irritate the skin.
- · After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: If symptoms persist consult doctor.
- $\cdot$  4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.
- · 4.3 Indication of any immediate medical attention and special treatment needed
  - No further relevant information available.

### SECTION 5: Firefighting measures

#### · 5.1 Extinguishing media

- Suitable extinguishing agents:
- CO2, powder or water spray. Fight larger fires with water spray or alcohol resistant foam.
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

### SECTION 6: Accidental release measures

- · 6.1 Personal precautions, protective equipment and emergency procedures Wear protective clothing.
- · 6.2 Environmental precautions: Dilute with plenty of water.
- Do not allow to enter sewers/ surface or ground water.
- · 6.3 Methods and material for containment and cleaning up:
- Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).
- 6.4 Reference to other sections See Section 7 for information on safe handling. See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

# SECTION 7: Handling and storage

· 7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace.

Safety data sheet



80 (var. colours)	
	(Contd. of page
· Information about fire - and explosion protection	<b>n:</b> No special measures required.
$\cdot$ 7.2 Conditions for safe storage, including any in	ncompatibilities
· Storage:	
<ul> <li>Requirements to be met by storerooms and receptac</li> <li>Information about storage in one common storage f</li> </ul>	
• Further information about storage conditions: Non	
· Storage class: 10	
• 7.3 Specific end use(s) No further relevant infor	rmation available.
SECTION 8: Exposure controls/personal p	rotection
SECTION 8. Exposure concrois/personal p	notection
· 8.1 Control parameters	and an at the second large s
• Ingredients with limit values that require monitor	<b>pring at the workplace:</b> ties of materials with critical values that have to
be monitored at the workplace.	
· Additional information: The lists valid during the	he making were used as basis.
· 8.2 Exposure controls	
<ul> <li>Appropriate engineering controls No further data;</li> <li>Individual protection measures, such as personal</li> </ul>	
<ul> <li>General protective and hygienic measures: Wash ha</li> </ul>	
· Respiratory protection: Not required.	
· Hand protection	
The glove material has to be impermeable and resi preparation.	istant to the product/ the substance/ the
Due to missing tests no recommendation to the glo	ove material can be given for the product/ the
preparation/ the chemical mixture. Selection of the glove material on consideration	of the penetration times, rates of diffusion and t
degradation	of the penetration times, faces of affasion and t
If only a short-term loading of the glove materia	
<pre>higher wearability for the better acceptance of t • Material of gloves</pre>	the users are recommended.
-	
The selection of the suitable gloves does not onl	lv depend on the material, but also on further mark
	ly depend on the material, but also on further mark acturer. As the product is a preparation of several
of quality and varies from manufacturer to manufa substances, the resistance of the glove material	acturer. As the product is a preparation of several
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application.	acturer. As the product is a preparation of several
of quality and varies from manufacturer to manufa substances, the resistance of the glove material	acturer. As the product is a preparation of several
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k</pre>	acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed.</pre>	acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k</pre>	acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and ha
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed.</pre>	acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper	acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information	acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling ties
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state	acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling ties roperties Fluid
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour:	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr General Information • Physical state • Colour:	acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour:	Acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr General Information • Physical state • Colour: • Odour:	acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined.
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing point:	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>Sties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity
of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>Tties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity)
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>Sties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit • Lower:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>Tties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity)
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out k to be observed. • Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit • Lower: • Upper:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out h to be observed. Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Flash point: Decomposition temperature: pH at 20 °C</pre>	Acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>ties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out b to be observed. Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Flash point: Decomposition temperature: pH at 20 °C Viscosity:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Secont content for the protective gloves and has therefore Not determined. Not determined. Secont content for the protective gloves and has therefore Not determined. Secont content for the protective gloves and has therefore Not determined. Secont content for the protective gloves and has therefore Not determined. Secont content for the protective gloves and has therefore Not determined. Secont content for the protective gloves and has therefore Not determined. Secont content for the protective gloves and has therefore Secont content for the protective gloves and has
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out b to be observed. Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>tties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. >93 °C Not determined. 6.5 Not determined.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit • Lower: • Upper: • Flash point: • Decomposition temperature: • pH at 20 °C • Viscosity: • Kinematic viscosity • Dynamic at 20 °C:</pre>	Acturer. As the product is a preparation of severa. can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>Prices</b> Fluid According to product specification Product specific Not determined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. 6.5
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR • Penetration time of glove material The exact break trough time has to be found out b to be observed. • Eye/face protection Goggles recommended during ref SECTION 9: Physical and chemical proper • 9.1 Information on basic physical and chemical pr • General Information • Physical state • Colour: • Odour threshold: • Melting point/freezing point: • Boiling point or initial boiling point and boiling range • Flammability • Lower and upper explosion limit • Lower: • Upper: • Flash point: • Decomposition temperature: • pH at 20 °C • Viscosity: • Kinematic viscosity • Dynamic at 20 °C: • Solubility</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>tties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out b to be observed. Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: PH at 20 °C Viscosity: Kinematic viscosity Dynamic at 20 °C: Solubility water:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas Fully miscible.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out h to be observed. Eye/face protection Goggles recommended during red SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic at 20 °C: Solubility water: Partition coefficient n-octanol/water (log value)</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas Fully miscible. Not determined.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out b to be observed. Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic at 20 °C: Solubility water:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undetermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas Fully miscible.
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out h to be observed. Eye/face protection Goggles recommended during red SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic at 20 °C: Solubility water: Partition coefficient n-octanol/water (log value)</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undeermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas Fully miscible. Not determined. 23 hPa (7732-18-5 water, distilled, conductivity
<pre>of quality and varies from manufacturer to manufa substances, the resistance of the glove material to be checked prior to the application. Nitrile rubber, NBR Penetration time of glove material The exact break trough time has to be found out h to be observed. Eye/face protection Goggles recommended during re SECTION 9: Physical and chemical proper 9.1 Information on basic physical and chemical pr General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic at 20 °C: Solubility water: Partition coefficient n-octanol/water (log value) Vapour pressure at 20 °C: Vapour pressure at 20 °C:</pre>	Acturer. As the product is a preparation of several can not be calculated in advance and has therefore by the manufacturer of the protective gloves and has efilling <b>rties</b> <b>roperties</b> Fluid According to product specification Product specific Not determined. Undeermined. 100 °C (7732-18-5 water, distilled, conductivity or of similar purity) Not applicable. Not determined. >93 °C Not determined. 6.5 Not determined. 400 mPas Fully miscible. Not determined. 23 hPa (7732-18-5 water, distilled, conductivity

(Contd. on page 4) EU

Safety data sheet



Trade name: QG 88xx Series; xx = 00; 01; 02; 03; 15; 10; 20; 21; 30; 31; 32; 40; 41; 50; 60; 61; 62; 70; 80 (var. colours)

	(Contd. of page
· Vapour density	Not determined.
• 9.2 Other information	The physical and chemical properties given in Section 9.1 are rough data only, which are partially derived from the component's data of th mixture. These data are no binding product specifications.
· Appearance:	0,00011104010.00
· Form:	Fluid
· Important information on protection of health	and
environment, and on safety.	-
· Auto-ignition temperature:	Product is not selfigniting.
· Explosive properties:	Not determined.
· Solvent content:	
· Organic solvents:	9.5 %
· Water:	42.3 %
· Solids content:	29.5 %
· Change in condition	
· Evaporation rate	Not determined.
· Information with regard to physical hazard	
classes	
· Explosives	none
· Flammable gases	none
· Aerosols	none
· Oxidising gases	none
· Gases under pressure	none
· Flammable liquids	none
· Flammable solids	none
$\cdot$ Self-reactive substances and mixtures	none
· Pyrophoric liquids	none
· Pyrophoric solids	none
<ul> <li>Self-heating substances and mixtures</li> </ul>	none
· Substances and mixtures, which emit flammable	
gases in contact with water	none
• Oxidising liquids	none
· Oxidising solids	none
· Organic peroxides	none
· Corrosive to metals	none
· Desensitised explosives	none

### SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

· Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

- 10.3 Possibility of hazardous reactions No dangerous reactions known.
- · 10.4 Conditions to avoid No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: No dangerous decomposition products known.

#### SECTION 11: Toxicological information

 $\cdot$  11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

- · Acute toxicity Based on available data, the classification criteria are not met.
- Skin corrosion/irritation Based on available data, the classification criteria are not met.
- · Serious eye damage/irritation Based on available data, the classification criteria are not met.
- · Respiratory or skin sensitisation May cause an allergic skin reaction.
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.
- · Carcinogenicity Based on available data, the classification criteria are not met.
- · Reproductive toxicity Based on available data, the classification criteria are not met. · STOT-single exposure Based on available data, the classification criteria are not met.
- · STOT-repeated exposure Based on available data, the classification criteria are not met.
- Aspiration hazard Based on available data, the classification criteria are not met.
- 11.2 Information on other hazards
- Endocrine disrupting properties

None of the ingredients is listed.

(Contd. on page 5)

ΕU



Trade name: QG 88xx Series; xx = 00; 01; 02; 03; 15; 10; 20; 21; 30; 31; 32; 40; 41; 50; 60; 61; 62; 70; 80 (var. colours)

(Contd. of page 4)

### SECTION 12: Ecological information

12.1 Toxicity

### • Aquatic toxicity: 18472-87-2 C.I. Acid Red 92

## EC50 / 48h 14.5 mg/l (Daphnie)

- · 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- · 12.4 Mobility in soil No further relevant information available.
- · 12.5 Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · vPvB: Not applicable.
- · 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- · 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Water hazard class 2 (German Regulation) (Self-assessment): hazardous for water Do not allow product to reach ground water, water course or sewage system. Danger to drinking water if even small quantities leak into the ground.

### SECTION 13: Disposal considerations

#### · 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

- · Uncleaned packaging:
- · Recommendation: Disposal must be made according to official regulations.
- · Recommended cleansing agents: Water, if necessary together with cleansing agents.

SECTION 14: Transport information	
<ul> <li>14.1 UN number or ID number</li> <li>ADR, ADN, IMDG, IATA</li> </ul>	not applicable
· 14.2 UN proper shipping name · ADR, ADN, IMDG, IATA	not applicable
<ul> <li>14.3 Transport hazard class(es)</li> <li>ADR, ADN, IMDG, IATA</li> <li>Class</li> </ul>	not applicable
· 14.4 Packing group · ADR, IMDG, IATA	not applicable
· 14.5 Environmental hazards:	Not applicable.
$\cdot$ 14.6 Special precautions for user	Not applicable.
<ul> <li>14.7 Maritime transport in bulk according to IMC instruments</li> </ul>	Not applicable.
· UN "Model Regulation":	not applicable

### SECTION 15: Regulatory information

· 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Directive 2012/18/EU

Named dangerous substances - ANNEX I None of the ingredients is listed.

· REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3

DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment - Annex II None of the ingredients is listed.

· REGULATION (EU) 2019/1148

Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

· Annex II - REPORTABLE EXPLOSIVES PRECURSORS

None of the ingredients is listed.

(Contd. on page

EU

Safety data sheet



None of Regulat:	(Contd. of <u>r</u> ion (EC) No 273/2004 on drug precursors the ingredients is listed.
None of Regulat:	
Regulat.	the ingredients is listed.
-	5
third co	ion (EC) No 111/2005 laying down rules for the monitoring of trade between the Community ountries in drug precursors
None of	the ingredients is listed.
Nationa.	l regulations:
Technica	al instructions (air):
Class	Share in %
NK	5-<10
	zard class: Water hazard class 2 (Self-assessment): hazardous for water. emical safety assessment: A Chemical Safety Assessment has not been carried out.
SECTIO	N 16: Other information
	formation is based on our present knowledge. However, this shall not constitute a guarant specific product features and shall not establish a legally valid contractual relationsh
	t phrases
	Toxic if swallowed.
	Harmful if swallowed.
H311 -	Toxic in contact with skin.
H312 I	Harmful in contact with skin.
НЗ14 (	Causes severe skin burns and eye damage.
	Causes skin irritation.
	May cause an allergic skin reaction.
H318 (	Causes serious eye damage.
НЗЗО .	Fatal if inhaled.
H335 I	May cause respiratory irritation.
	Very toxic to aquatic life.
	Very toxic to aquatic life with long lasting effects.
	Corrosive to the respiratory tract.
Date of	previous version: 19.08.2021
Abbrevia	ations and acronyms:
ADR: Accor	d relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the Interna
	f Dangerous Goods by Road)
	rrnational Maritime Code for Dangerous Goods
	rnational Air Transport Association
	lly Harmonised System of Classification and Labelling of Chemicals
	ropean Inventory of Existing Commercial Chemical Substances ropean List of Notified Chemical Substances
	ropean List of Notified Chemical Substances cal Abstracts Service (division of the American Chemical Society)
	start, Bioaccumulative and Toxic
	· Persistent and very Bioaccumulative
	3: Acute toxicity - Category 3
	4: Acute toxicity - Category 4
Acute Tox.	2: Acute toxicity - Category 2
Skin Corr.	1: Skin corrosion/irritation - Category 1
	2: Skin corrosion/irritation - Category 2
Skin Irrit	: Serious eye damage/eye irritation - Category 1
Skin Irrit Eye Dam. 1	
Skin Irrit Eye Dam. 1 Skin Sens.	1: Skin sensitisation - Category 1
Skin Irrit Eye Dam. 1 Skin Sens. Skin Sens.	1A: Skin sensitisation - Category 1A
Skin Irrit Eye Dam. 1 Skin Sens. Skin Sens. Skin Sens.	1A: Skin sensitisation - Category 1A 1B: Skin sensitisation - Category 1B
Skin Irrit Eye Dam. 1 Skin Sens. Skin Sens. Skin Sens. STOT SE 3:	1A: Skin sensitisation - Category 1A 1B: Skin sensitisation - Category 1B Specific target organ toxicity (single exposure) - Category 3
Skin Irrit Eye Dam. 1 Skin Sens. Skin Sens. Skin Sens. STOT SE 3: Aquatic Ac	1A: Skin sensitisation - Category 1A 1B: Skin sensitisation - Category 1B Specific target organ toxicity (single exposure) - Category 3 ute 1: Hazardous to the aquatic environment - acute aquatic hazard - Category 1
Skin Irrit Eye Dam. 1 Skin Sens. Skin Sens. StOT SE 3: Aquatic Ac Aquatic Ch	1A: Skin sensitisation - Category 1A 1B: Skin sensitisation - Category 1B Specific target organ toxicity (single exposure) - Category 3